

## Shanghai Chenxu Trading Co.,ltd

ADD: Room 531 Buillding 37 No., 2049 Road, Minhang District, Shanghai, CHINA. 201104

Product	4N 99.99% high purity Alumina Slurry
	4N 99.99% high purity aluminum oxide Slurry

**Description:** As a coating, 4N 99. 99% high purity Alumina Slurry (aluminum oxide Slurry) is applied to the diaphragm between the positive and negative poles of lithium battery to play the role of heat resistance, high temperature resistance and insulation, so as to prevent the short circuit of power battery due to too high temperature.

## Picture:



Foreign trade director: Andy Zhang Web: www.sh-alumina.com

First

TEl:+86-(0)21-60879750 Email: info@sh-alumina.com



## Shanghai Chenxu Trading Co.,ltd

ADD: Room 531 Buillding 37 No.,2049 Road, Minhang District, Shanghai, CHINA. 201104

## Specifications:

4N high purity Alumina Slurry (aluminum oxide Slurry)								
Туре			CX009A	СХ009В	CX009C			
Crystal form			α	α	α			
Solid content		%	40-60	40-60	40-60			
Viscosity (20℃),		Pa.s	0.04-0.5	0.04-0.5	0.04-0.5			
PH value			7-9	7-9	7-9			
Contact angle(20℃)			42-53	42-53	42-53			
	partic]	le size	um	1.2	1.2	1.2		
particle size	(D50) ≤							
	particle size		um	2.4	2. 4	2.4		
	(D90	))≤						
Al203 Content		%	≥99.9	≥99.99	≥99.995			
Content of Impurities		Na	ppm	500	10	5		
		Mg	ppm	20	2	2		
		Ca	ppm	20	2	2		
		K	ppm	5	2	1		
		Si	ppm	50	10	5		
		Fe	ppm	50	10	5		
		Zn	ppm	5	2	1		
		Mn	ppm	5	2	1		

Application: 4N 99.99% high purity alumina slurry (aluminum oxide slurry) was widely used for adsorbent, lithium battery diaphragm, special ceramics and so on

 $\mathtt{OEM}: \mathtt{We}\ \mathtt{also}\ \mathtt{have}\ \mathtt{other}\ \mathtt{type}\ \mathtt{4N}\ \mathtt{and}\ \mathtt{5N}\ \mathtt{high}\ \mathtt{purity}\ \mathtt{alumina/aluminum}\ \mathtt{oxide}\ \mathtt{powder},$  contact with us for  $\mathtt{OEM}$ 

Foreign trade director: Andy Zhang Web: www.sh-alumina.com

Second

TE1:+86-(0)21-60879750 Email: info@sh-alumina.com